

SUZHOU AOKE RUBBER TECHNOLOGY LTD.

NO.4 TONGXIN EAST ROAD,WANPING TOWN,WUJIANG DISTRICT CITY SUZHOU,JIANGSU PROVINCE,CHINA.

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : SILICONE STRAW
SGS Ref No. : CANHG1917451601
Style / Item No. : AOKE-20190901
Sample Receiving Date : Sep. 2, 2019
Test Performing Date : Sep. 2, 2019 to Sep. 10, 2019
Test Performed : Selected test(s) as requested by applicant
Test Result(s) : For further details, please refer to the following page(s)

Result Summary :

Test Requested

Conclusion

FDA 21 CFR 177.2600–Total extractive residues

PASS

Conclusion : The tested parameters comply with the requirement stated in Food and Drug Administration Regulations

Signed for and on behalf of
Xiamen Branch, SGS-CSTC Co., Ltd.



Beck Hong
Approved Signatory



SGS-CSTC Inspection & Testing Services Co., Ltd.
Xiamen Branch Testing Center Hardlines

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101 t (86-592) 5766537 f (86-592) 5766460 www.sgsgroup.com.cn
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101 t (86-592) 5766537 f (86-592) 5766460 e sgs.china@sgs.com

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description	Material (claimed by the client)
SN1	CAN19-174516.001	silicone straw	Silicone rubber

FDA 21 CFR 177.2600–Total extractive residues

Test Method : With reference to US FDA 21 CFR 177.2600.

<u>Simulant Used</u>	<u>Time</u>	<u>Temperature</u>	<u>Max. Permissible Limit</u>	<u>Result of 001</u>	<u>Comment</u>
Distilled Water	7.0hr(s)	Reflux temperature	20mg/sq. in	<0.5mg/sq. in	PASS
Succeeding Extraction	2.0hr(s)	Reflux temperature	1mg/sq. in	<0.5mg/sq. in	PASS
n-Hexane	7.0hr(s)	Reflux temperature	175mg/sq. in	27.0mg/sq. in	PASS
Succeeding Extraction	2.0hr(s)	Reflux temperature	4mg/sq. in	3.3mg/sq. in	PASS


Notes :

mg/inch²= milligram per square inch

Remark: This test was subcontracted to Guangzhou Branch, SGS-CSTC Co., Ltd.



Sample photo(s):



CANHG1917451601

CAN19-174516.001

The testing report/certificate only refers to the sample(s) tested.

End of Report

