



TEST REPORT

Test Report # 18H-005779 Date of Report Issue: August 28, 2018
 Date of Sample Received: August 2, 2018 Pages: Page 1 of 15

CLIENT INFORMATION:

Company: Imagen Brands
 Recipient: Carissa Roepke
 Recipient Email: CarissaR@imagenbrands.com



SAMPLE INFORMATION:

Description:	Magnetic Bookmark	Purchase Order Number:	-
Assortment:	Standard, Big, Paws N Claws	Toy Co./Agency:	-
SKU/style No.:	VT7900 Standard Magneticmark Bookmark / VT7901 Big Magneticmark Bookmark / VT7908 Paws N Claws Magneticmark Bookmark / VT7900, VT7901, VT7908		
Factory/Supplier/Vendor:	MMP021479	Country of Origin:	Mexico
Country of Distribution:	United States, Canada	Labeled Age Grade:	-
Quantity Submitted:	1 pc per style + 2 lot Paints	Requested Age Grade:	6+
Testing Period:	08/07/2018 – 08/28/2018	Tested Age Grade:	Over 6 years of age

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka
 Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
 This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Paints and Similar Surface Coatings
PASS	CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Substrate Materials
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP) [#]
PASS	Canadian Toys Regulations SOR/2011-17 as Amended by SOR/2016-195 & SOR/2016-302, Item 23 Leachable Elements in Paints and Surface Coatings
PASS	Canadian Toys Regulations SOR/2011-17 as Amended by SOR/2016-195 & SOR/2016-302, Item 23 Total Lead and Mercury in Paints and Surface Coatings

**DETAILED RESULTS:****CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Paints and Similar Surface Coatings**

Test Method: ASTM F963-17 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	1	2	3	4	8	Soluble Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	140	650	100	120	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Lead (Pb)	ND	ND	ND	ND	ND	90
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

Remark:

Test portion of Specimen No. 4 found on single sample was 71.8 mg.

**DETAILED RESULTS:****CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Substrate Materials**

Test Method: ASTM F963-17 Clause 8.3.5

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Substrate Materials Other than Modeling Clay

Specimen No.	5	6	7	---	---	Soluble Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Soluble Antimony (Sb)	ND	ND	ND	---	---	60
Soluble Arsenic (As)	ND	ND	ND	---	---	25
Soluble Barium (Ba)	ND	8	5	---	---	1000
Soluble Cadmium (Cd)	ND	ND	ND	---	---	75
Soluble Chromium (Cr)	ND	ND	ND	---	---	60
Soluble Lead (Pb)	ND	ND	ND	---	---	90
Soluble Mercury (Hg)	ND	ND	ND	---	---	60
Soluble Selenium (Se)	ND	ND	ND	---	---	500
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

**DETAILED RESULTS:****CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings**

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	8	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	6	7	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	23	---	---	100
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	3	4	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	200	ND	LT 260	LT 250	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	LT 260	LT 250	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	220	260	500	430	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	LT 260	LT 250	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	LT 260	LT 250	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	LT 260	LT 250	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		5	6	7	8	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**Test Method: CPSC-CH-C1001-09.3 (Modified)[#], In-House Method[#]

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	3	4	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	200	ND	LT 260	LT 250	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	LT 260	LT 250	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	220	260	500	430	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	LT 260	LT 250	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	LT 260	LT 250	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	LT 260	LT 250	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	LT 260	LT 250	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	LT 260	LT 250	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**Test Method: CPSC-CH-C1001-09.3 (Modified)[#], In-House Method[#]

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		5	6	7	8	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Canadian Toys Regulations SOR/2011-17 as Amended by SOR/2016-195 & SOR/2016-302, Item 23
Leachable Elements in Paints and Surface Coatings**

Test Method: Health Canada Method C-03 (Effective 2014-02-20)

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	1	2	3	4	8	Leachable Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Leachable Antimony (Sb)	ND	ND	ND	ND	ND	1000
Leachable Arsenic (As)	ND	ND	ND	ND	ND	1000
Leachable Barium (Ba)	ND	ND	ND	ND	ND	1000
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	1000
Leachable Selenium (Se)	ND	ND	ND	ND	ND	1000
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 50 ppm)

**DETAILED RESULTS:****Canadian Toys Regulations SOR/2011-17 as Amended by SOR/2016-195 & SOR/2016-302, Item 23 Total Lead and Mercury in Paints and Surface Coatings**

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	8	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Total Mercury (Hg)	ND	ND	ND	ND	ND	10
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Black paint	Paint (Paints style)
2	Yellow paint	Paint (Paints style)
3	Red paint	Paint (Paints style)
4	Blue paint	Paint (Paints style)
5	White card paper	Raw material (CARD 14PTS style)
6	White PVC	Raw material (WALLDECO MATERIAL style)
7	Black soft plastic	Raw material (FLEXIBLE MAGNET style)
8	Transparent paint	Paint (Paints style)



Test Report #

18H-005779

Pages:

Page 14 of 15

SAMPLE PHOTO:



ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #

18H-005779

Pages:

Page 15 of 15

SAMPLE PHOTO:



-End Report-

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.